

artisan EXTERIOR

Geotech Summary - Crazy Paving

	Weight	Size Tolerance		Slip Resistance	Strength		Salt Resistance**	Crystalline Silica Tests	Absorption	
	30mm /m2	Dimension	Thickness		Compressive Strength	Flexural Strength	TBC		Water Absorption %	Open Porosity %
20mm Crazy										
Bluestone	45	+/- 2mm	+/- 2mm	P5	132.6 MPa	21.2 MPa		51% *	1.07%	0.60%
Kahvi	45	+/- 2mm	+/- 2mm	P4	105 MPa	15.4 MPa	0.25%	2.16%	0.91%	2.02%
Harmaa	45	+/- 2mm	+/- 2mm	P5				<1%	0.15%	1.14%
Nevoa	45	+/- 2mm	+/- 2mm	P5	66 MPa	6.33 Mpa	0.22%	3.64%	1.34%	2%
Sokeria	45	+/- 2mm	+/- 2mm	P5	105 MPa	15.4 MPa	0.25%	2.16%	0.91%	2.02%
Valas	54	+/- 2mm	+/- 2mm	P4	52 Mpa	14 MPa		<1%	0.15%	1.14%
Split Crazy Paving										
Arkkia	78	+/- 2mm	+/- 2mm	P4				73%		
Calor	81	+/- 2mm	+/- 2mm	P4	22 Mpa	14.26 Mpa		94%	0.30%	0.80%
Porphyry	80	+/- 2mm	+/- 2mm	P5	178 Mpa	24 Mpa		74%	0.70%	

For more information contact your Artisan Exterior Account Manager or call 1300 301898

www.artisanexterior.com.au

* Estimated awaiting further testing

** Total mass lost over 15 cycles