

GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD

26a Production Avenue Kogarah NSW 2217 AUSTRALIA ABN: 13 622 802 797

T. 1300 01 GRIP E. info@griptek.com.au

Test Report No: 190418C

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: Artisan Exterior - PO Box 4088 Kingston ACT 2604

Test Date: 19-04-2018 **Temperature:** 26 deg c.

Test Conducted to: AS 4586:2013 Appendix A **Conducted by:** Sebastian Silva

Test Method: Wet Pendulum Testing Test Device: Munro S/N - 1509

Surface: Matala Rubber Slider Used: Slider 96 (4 S Rubber)

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

Test Location: Artisan Exterior - 23 Harris Street, Pyrmont NSW 2009

Surface Preparation: Cleaned with Water & Scrubbing

Surface Application: N/A.

Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found		N/A	50
2	Loose Sample	As Found	<2.0	N/A	49
3	Loose Sample	As Found	<2.0	N/A	50
4	Loose Sample	As Found	<2.0	N/A	51
5	Loose Sample	As Found	<2.0	N/A	50

Mean BPN Slip Resistance Value - SRV 50

Classification P4

Contribution to Risk Low

Interpretation of the Wet Pendulum Results					
Classification of pedestrian surface materials according to the AS 4586	Mean BPN				
P5	>54				
P4	45-54				
P3	35-44				
P2	25-34				
P1	12-24				
P0	<12				

Approved Signatory: Michael Holt

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.